



Super Duplex — ASTM A995 6A

Standard Specification for Castings, Austenitic-Ferritic (Duplex) Stainless Steel, for Pressure-Containing Parts

MATERIAL DATASHEET

GROUP
Ferrous Stainless Steel Alloys

SUB GROUP
ASTM A995 / A995M

INDUSTRY
Investment Casting

This pressure-grade duplex casting alloy uniquely combines tungsten and copper alongside chromium, nickel, molybdenum, and nitrogen to create superior resistance to both oxidizing and reducing corrosive environments. The dual austenitic-ferritic microstructure delivers an exceptional balance of high tensile strength and 25% elongation, ensuring reliable performance under demanding pressure conditions. Solution annealing optimizes the phase balance, making it the preferred choice for critical pressure-containing valves, pumps, and industrial casting applications.



CHEMICAL COMPOSITION

ELEMENT	SYMBOL	COMPOSITION
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.030 max.
Sulphur	S %	0.025 max.
Chromium	Cr %	24.000 – 26.000
Nickel	Ni %	6.500 – 8.500
Molybdenum	Mo %	3.000 – 4.000
Copper	Cu %	0.500 – 1.000
Nitrogen	N %	0.200 – 0.300
Tungsten	W %	0.500 – 1.000
Iron	Fe %	Balance



MECHANICAL PROPERTIES

PERFORMANCE SPECIFICATIONS

Tensile Strength **690**
Minimum Value MPa

Yield Strength **450**
Minimum Value MPa

Elongation **25**
Minimum Value %



HEAT TREATMENT
Solution Annealing



INDUSTRY APPLICATIONS

Offshore oil & gas



Chemical process industries



Seawater systems



Marine engineering



Pressure-containing pump



DISCLAIMER: All information in this datasheet is indicative only and is not intended to be a substitute for the full specification. It provides typical values for comparison between metal alloy options rather than a definitive statement of mechanical performance. Values may vary with temperature, product type, and application. This data does not constitute any guarantee of properties.

Tamboli Castings Limited

Bhavnagar, Gujarat, India

Phone: +91 278 2541000

Email: info@tambolicastingslimited.com